

TEST REPORT



APPLICANT : SHIN SUNG CO., LTD.

REPORT NO. : H214-17-33609

SAMPLE RECEIVED DATE : 2017-11-06

TEST STARTED DATE : 2017-11-06

REPORT ISSUED DATE : 2017-11-08


PAGE : 1 OF 2

DESCRIPTION : ONE(1) GROUP OF SUBMITTED SAMPLE SAID TO BE THREAD.

ITEM : 1680D BLACK


TEST CONDUCTED : AS REQUESTED BY THE APPLICANT, FOR DETAILS PLEASE SEE ATTACHED PAGES.

PREPARED AND CHECKED BY
FOR FITI



HYUN-JIN, KOO
QUALITY MANAGER

AUTHORIZED BY
FOR FITI



KYUNG-YOON SON
PRESIDENT

※ Report Verification No.:

(You can see the authenticity of your test report through the above "Report Verification No." at FITI homepage.)

e-DOCUMENT SERVICE

The test results contained in this report are limited to results on the sample(s) that is provided by client and are not necessarily indicative or representative of the qualities of the lot from which the sample(s) was taken or of all products. Results contained in this report are not based on the quality certification of sample by the FITI quality certification program unless specifically requested by the client. Further use of the results of this report is prohibited unless allowed under a separate agreement set forth in an official document that is established between the client identified on this letter and the FITI.

REPORT NO. : H214-17-33609
PAGE : 2 OF 2

01. YARN STRENGTH (ASTM D2256/D2256M-10e1 : 2015, C.R.E) : cN/Denier(gf/Denier)

	#1
	6.77 (6.90)

NOTE) THE PRACTICAL UNIT gf/Denier WAS EXPRESSED TOGETHER WITH cN/Denier BY CLIENT'S REQUEST.
THE CONVERSION FACTOR FOR cN/Denier FROM gf/Denier UNIT IS 0.980 665.

02. YARN ELONGATION (ASTM D2256/D2256M-10e1 : 2015, C.R.E) : %

	#1
	21.6

**** End of The Report ****

e-DOCUMENT SERVICE

The test results contained in this report are limited to results on the sample(s) that is provided by client and are not necessarily indicative or representative of the qualities of the lot from which the sample(s) was taken or of all products. Results contained in this report are not based on the quality certification of sample by the FITI quality certification program unless specifically requested by the client. Further use of the results of this report is prohibited unless allowed under a separate agreement set forth in an official document that is established between the client identified on this letter and the FITI.